



Kimia Baspar Golpa

PA6FRG630

PA6+Flame Retardant+Glass Fiber

General Information

● **Characteristic:** Injection grade, Medium Impact, Flame Retardant, Glass Fiber Reinforced

Physical Property

Property	Test method	Test condition	Unit	Nominal Values
----------	-------------	----------------	------	----------------

Mechanical Property

Notched Izod impact	ASTM D256	23°C, 3.2mm	KJ/m2	8
Rock well hardness	ASTM D-785	R-Scal	R-Scal	81
Tensile Strength at yield	ASTM D638	23°C, 50 mm/min	Mpa	145
Elongation at break			%	3
Flexural modulus	ASTM D790	23°C 10mm/min	Mpa	7000
Flexural strength			Mpa	180

Flammability

Flammability	UL94	¼ inch (3.2 mm)	V-0 (<76mm/min)	V-0
--------------	------	-----------------	-----------------	-----

Thermal Property

HDT(Heat Deflection Temp)	ASTM D648	unannealed 0.46MPa	°C	210
HDT(Heat Deflection Temp)	ASTM D648	unannealed 1.8MPa	°C	200

Polymer property

Melting Point	DSC Method		°C	260
Filler content	ASTM D5630-94	800°C	%	35
Density	ASTMD792	23°C	g/cm3	1.4
Mold shrinkage	ASTM D955	100*100*3.2 mm	%	0.3~0.6
Water Absorption	ASTM D570	23°C, water, 24h	%	1.3

Electrical

Dielectric Strength	ASTM D149		Kv/mm	...
Volume Resistivity	ASTM D257		Ω.cm	
Dielectric Constant	ASTM D150		10 ⁶ HZ	

1-typical values are not our specification and not be used for part or tool design.

2-all properties, except Melt Flow Index are measured on injection molded specimens and after 48 hour storage at 23°C and in RH of 50%..

www.kbgco.ir

PA6FRG630	PA6+Flame Retardant+Glass Fiber
------------------	--

Processing guid (Injection molding condition)
--

Processing parameters	unit	value
Drying Temperature	°C	70~80
Drying Time	hrs	2~4
Moisture content	%	<0.1
Melt Temperature	°C	220
Cylinder Temperature	Reare	°C 220~230
	Middle	°C 230~260
	Front	°C 230~260
Nozzel Temperature	°C	230~260
Mold Temperature	°C	70~80
Injection Pressure	kg/cm2	60~150
Screw Speed	rpm	30~60

Note): Some modifications may be required depending on the specific molding equipment and part configuration.

www.kbgco.ir